
Technical Report of INR18650-35E



SAMSUNG

SAMSUNG SDI

June, 2015

Cylindrical cell development group
Energy Business Division
SAMSUNG SDI

This material is proprietary to Samsung SDI Co., Ltd. It shall not be used, reproduced, copied, disclosed, transmitted, in whole or in part, without the express written consent of Samsung SDI Co., Ltd.



SAMSUNG

SAMSUNG SDI

Tentative Specification of INR18650-35E

PROPRIETARY AND
CONFIDENTIAL

Φ max 18.50 mm




Max
65.25 mm

With Tube

		INR18650-35E
● Capacity (0.2C)	Typical Min.	3450mAh 3350mAh
● Nominal Voltage (0.2C)		3.60V
● Charging Method		CC-CV
● Charging Voltage		4.20V
● Charging Current	Max.	1500mA
● Discharging Cut-off Voltage		2.50V
● Discharging Current (Not for cycle)	Max.	8000mA
● Weight	Max.	50.0g
● Operating Temperature	Charge Discharge	0 ~ 45 °C -10 ~ 60 °C
● Storage Temperature	1 Year 3 Months 1 Month	-20 ~ 25 °C -20 ~ 45 °C -20 ~ 60 °C

Standard Capacity_0.2C



PROPRIETARY AND
CONFIDENTIAL



capacity (mAh)	Energy (Wh)
3,482	12.62

Cycle Life_1C cycle

PROPRIETARY AND
CONFIDENTIAL




SDI private

Cycle Life_1C cycle at 45°C

PROPRIETARY AND
CONFIDENTIAL


INR18650-35E Cycle Life at 45 °C

Model : INR18650-35E [1C A = 3,400 mA]
Method : Charge CC-CV 0.3C 4.2V 0.05C cut off, rest 5min. at 45°C
Discharge CC 1.0C 2.65V cut off, rest 5min. at 45°C 500cyc



INR18650-35E Cycle Life at 45°C


Model : INR18650-35E [1C A = 3,400 mA]
Method : Charge CC-CV 0.3C 4.2V 0.05C cut off, rest 5min. at 45°C
Discharge CC 1.0C 2.65V cut off, rest 5min. at 45°C 500cyc



SDI private

Room Temperature Discharge (23°C)

PROPRIETARY AND
CONFIDENTIAL




	3.5A	7.0A	10.0A
Capacity (mAh)	3,468	3,429	3,379
Energy (Wh)	11.94	11.37	10.98

Storage at 60°C (SOC100)

PROPRIETARY AND
CONFIDENTIAL


AC-IR

Change in AC Impedance during Storage at 60°C



DC-IR

Change in DC IR during Storage at 60°C



Storage day	Initial		After storage		Ratio		
	AC-IR	DC-IR	AC-IR	DC-IR	AC-IR	DC-IR	Recovery
10	19.8	34.5	20.8	36.1	105.4	104.5	98.0
20			20.9	37.8	105.0	110.2	97.4

Safety Test Results

PROPRIETARY AND
CONFIDENTIAL

Tests	Requirements	Results	OK/NG
Overcharge (1C, 3hr)	L1	4L0	OK
Hot oven (140 °C)	L1	3L1	OK
Crush (13 kN)	L3	10L1	OK
Impact (ϕ 15.8, 9.1kg, 610mm)	L3	10L0	OK
External short Circuit @55 °C (20m Ω)	L1	5L0	OK
Forced-Discharge	L3	5L0	OK

Level	Criteria
L0	No change
L1	Leak
L2	Smoke, <200 °C
L3	Smoke, >200 °C
L4	Fire
L5	Explosion

- Thank you -

SAMSUNG

SAMSUNG SDI